PRODUCT INFORMATION





SCHWEIGHOFER SOLID®

primed 5 layers, HDF deck double core light wood



Core: double core from light wood

Face deck: 3 mm HDF

Primer film: special film overlay impregnated with aminoplastic resins

Primer film color: white; grey upon request

Gluing: E1, E0 on request

Thicknesses: 39,4 mm

Weight: 418 kg/ m³

Standard sizes: 5200 x 2000 mm

Moisture content: 8 – 12%

Thickness tolerance: + 0,2 mm - 0,6 mm

Tolerance in length: +/- 2 mm/m
Tolerance in width: +/- 5mm/m
Squareness tolerance: 1 mm/m

Thickness in mm	E-Modul (N/mm²) (length)	E-Modul (N/mm²) (width)	Bending strength (N/mm²) (length)	Bending strength (N/mm²) (width)
39,4	2441	6200	17	35

Multiple applications

Holzindustrie Schweighofer BACO offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives.

Additionally we develop solutions

together with our customers,

according to their individual

requirements.

Significant advantages

- * High stability and moisture resistance
- * High bending strength
- * Light weight
- * High screw extraction resistance
- * Easy processing

High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards. Continuous quality controls ensure stable standards.

All wood that is processed by Holzindustrie Schweighofer BACO comes from PEFC controlled sources. Some of our products are available with FSC® certifications.

S.C. Holzindustrie Schweighofer BACO S.R.L. Strada Crinului 15, 605200 Comanesti, Romania

T: +40 234 374 052 F: +40 234 374 622 baco.sales@schweighofer.ro www.schweighofer.ro www.schweighofer.at